Technical Data Sheet **Manufacturer handbook data**

Revision 01 | 02 November 2026 | English

TPR Surface Treatment Agent

Preparation & cleaners

FIELD OF APPLICATION

For pretreating TPR surfaces.

CHARACTERISTICS

Surface cleaning and adhesion preparation.

MATERIAL AND PROCESS

Process route: Surface preparation

Material references: TPR

SELECTION NOTE

Confirm the exact supplied grade, substrate finish and complete system before a production trial. This document translates handbook information; it does not certify performance on every material.

REPORTED PRODUCT DATA

Property	Handbook information
Pack size	16 kg
Stated shelf life	12 months
Adhesion	Cross-cut test mentioned; rating not stated
Abrasion test	RCA≥50 cycles(175g)
Alcohol rub test	Anhydrous ethanol, 500 g load, 100 rubs; method not stated
Salt-spray test	5% NaCl, pH 5.5 / 8.0, 48 h; method not stated
Petrol resistance	Petrol exposure for 24 h; method not stated
Pencil-hardness test	Pencil test at 45 degrees / 500 g; hardness result not stated

Reported values retain source limitations. Test methods, sample preparation and conditions must be confirmed before using a result as a production acceptance criterion.

Revision 01 | 02 November 2026 | English

TYPE OF PACKING

16 kg.

SHELF LIFE AND STORAGE

Stated shelf life: 12 months.

Confirm storage temperature, container conditions and batch dating with the supplier. Shelf life is not the working time after components have been mixed.

APPLICATION REVIEW

Provide the material, intended operation, existing surface treatment and required result when requesting technical advice.

Obtain the current grade-specific instructions for compatible additives, application settings, drying and final conditioning. Carry out a trial on the actual construction before a commercial run.

COLOUR AND FINISH

Where relevant, provide the target colour and finish together with a substrate sample. This sheet does not assign colour codes or availability that are absent from the source.

PRECAUTIONS

1. Use the current exact-grade SDS for handling, storage, transport and disposal. This TDS does not replace the SDS.

2. Follow the SDS and site procedures for protective equipment, ventilation, spills and waste.

3. Confirm product and material compatibility. Do not treat a method-only entry or an unspecified unit as an approved result.

4. Regulatory or restricted-substance conformity requires the relevant report and scope. General handbook wording is not an independent certification.

TECHNICAL CONTACT

StrideChem
Manufacturing in China
Email: alex@stridechem.in
WhatsApp: +86 177 5965 5021

Contact the technical team

DOCUMENT BASIS

English product information based on the supplied Yunrui manufacturer technical handbook. Technical review copy; unresolved source details have not been invented.

SC-TDS-013 | Revision 01